Technical Specification Code: 3.4.B(2) Polished



Eco Friendly Tiles Ltd Ground Floor, Solon House 40a Peterborough Road London SW6 3BN

0844 980 2233 info@ecofriendlytiles.co.uk

www.ecofriendlytiles.co.uk

			<u> </u>
Physical & Chemical Properties	Norm/Test Method	Required Standard	Results
Length & Width	ISO 10545-2	± 0.5%	± 0.1%
Thickness	ISO 10545-2	± 5%	± 4%
Straightness of Edges	ISO 10545-2	± 0.5%	± 0.1%
Planarity/Flatness	ISO 10545-2	± 0.5%	± 0.1%
Water Absorption	ISO 10545-3	≤ 0.5%	0.05%
Flexural Resistance	ISO 10545-4	Min. 35 N/mm²	$50N/mm^2 = 509 \text{ kg/cm}^2$
Modulus of Rupture	ISO 10545-4	1300N	2500 - 5000N
Deep Abrasion Resistance	ISO 10545-6	≤ 175mm²	140mm²
Coefficient of Thermal Expansion	ISO 10545-8	Available on request	≤ 7x10 -6 °C-1
Thermal Shock Resistance	ISO 10545-9	Available on request	Resistant
Frost Resistance	ISO 10545-12	Always Tested	Resistant
Resistance to Household Chemicals	ISO 10545-13	min. UB	min.UB
Resistance to Acids and Low Concentration Alkalis	ISO 10545-13	DA ULA, ULB A ULC	DA ULA, ULB A ULC
Resistance to Acids and High Concentration Alkalis	ISO 10545-13	Available on request	Available
Stain Resistance	ISO 10545-14	Available on request	min.3
Colour Stability to Light	DIN 51094	No visible colour varitaion allowed	Conforms
Coefficient of Friction	DIN 51130	-	-
	ASTM C1028/96	-	-
	BCR rep.CEC 6/81	-	-
	DIN 51097	-	-

Certifications













