Technical Specification Code: 5.2.A(2)G Previously VT.97G



Eco Friendly Tiles Limited Ground Floor, Solon House 40a Peterborough Road London SW6 3BN

0844 980 2233 info@ecofriendlytiles.co.uk

www.ecofriendlytiles.co.uk

			,
Physical & Chemical Properties	Norm/Test Method	Required Standard	Results
Thickness	EN ISO 10545-2	± 5.0% / ± 0.5mm	Conforms
Straightness of sides	EN ISO 10545-2	± 0.5% / ± 1.5mm	Conforms
Rectangularity	EN ISO 10545-2	± 0.6% / ± 2.0mm	Conforms
Surface Flatness	EN ISO 10545-2	± 0.5% / ± 2.0mm	Conforms
Water Absorption	EN ISO 10545-3	≤ 0.5%	0.05%
Flexion Resistance	EN ISO 10545-4	S ≥ 700 N (< 7.5mm)	S 3.000 N
		R ≥ 35 N/mm ²	R ≥ 53 N/mm ²
Impact Resistance	EN ISO 10545-5	Declared Value	0.87
Abrasion Resistance	EN ISO 10545-6	≤ 175mm2	135mm²
Coefficient of Linear Thermal Expansion	EN ISO 10545-8	-	∂ = 7 x 10 ⁻⁶ °C ⁻¹
Resistance to Thermal Shocks	EN ISO 10545-9	Pass according to EN ISO 10545-1	No Damage
Frost Resistance	EN ISO 10545-12	Pass according to EN ISO 10545-1	No Damage
Resistance to Chemicals	EN ISO 10545-13	UB Min.	UA ULA UHA
Resistance to Stains	EN ISO 10545-14	Declared Value	Class 5
Lead and Cadmium Discharge	EN ISO 10545-15	Declared Value	Within Limit
Slip Resistance	DM. 236/89 BCRA	> 0.40	> 0.40
	ASTM Wet and Dry	> 0.60	> 0.60
	DIN 51130	-	R12
	DIN 51097	-	A+B+C
Pendulum Test	UNI EN 13036-4:2011	≥36	≥ 36

Certifications















