Technical Specification Code: VT.220 Grip



Eco Friendly Tiles Ltd Ground Floor, Solon House 40a Peterborough Road London SW6 3BN

0844 980 2233 info@ecofriendlytiles.co.uk

www.ecofriendlytiles.co.uk

				WWW.ccomenarythes.co.ak
Physical & Chemical Properties	Norm/Test Method	Required Standard	Results	
Thickness	EN ISO 10545-2	± 5.0% / ± 0.5mm	Conforms	
Straightness of sides	EN ISO 10545-2	± 0.5% / ± 1.5mm	Conforms	
Rectangularity	EN ISO 10545-2	± 0.6% / ± 2.0mm	Conforms	
Surface Flatness	EN ISO 10545-2	± 0.5% / ± 2.0mm	Conforms	
Water Absorption	EN ISO 10545-3	≤ 0.5%	0.03%	
Flexion Resistance	EN ISO 10545-4	S ≥ 700 N (< 7.5mm)	S 3.038 N	
		$R \ge 35 \text{ N/mm}^2$	R ≥ 50.5 N/mm ²	
Impact Resistance	EN ISO 10545-5	Declared Value	0.88	
Abrasion Resistance	EN ISO 10545-6	≤ 175mm2	124mm³	
Coefficient of Linear Thermal Expansion	EN ISO 10545-8	-	$\partial = 7.3 \times 10^{-6} ^{\circ}\text{C}^{-1}$	
Resistance to Thermal Shocks	EN ISO 10545-9	Pass according to EN ISO 10545-1	No Damage	
Frost Resistance	EN ISO 10545-12	Pass according to EN ISO 10545-1	No Damage	
Resistance to Chemicals	EN ISO 10545-13	UB Min.	UA ULA UHA	
Resistance to Stains	EN ISO 10545-14	Declared Value	Class 5	
Lead and Cadmium Discharge	EN ISO 10545-15	Declared Value	Within Limit	
Slip Resistance	DM. 236/89 BCRA	> 0.40	> 0.40	
	ASTM Wet and Dry	> 0.60	> 0.60	
	DIN 51130	-	R11	
	DIN 51097	-	A+B+C	
Pendulum Test	UNI EN 130036	≥36	≥36	

Certifications













