Technical Specification Code: VA.125



Eco Friendly Tiles Ltd Ground Floor, Solon House 40a Peterborough Road London SW6 3BN

0844 980 2233 info@ecofriendlytiles.co.uk

www.ecofriendlytiles.co.uk

| Physical & Chemical Properties | Norm/Test Method | Required Standard | Results | |
|---|------------------|---------------------|--------------------------|--|
| Thickness | ISO 10545-2 | ± 0.3%, ± 10% | ± 0.2% | |
| Straightness of Edges | ISO 10545-2 | ± 0.3% | ± 0.4% | |
| Squareness | ISO 10545-2 | ± 0.5% | ± 0.4% | |
| Flatness | ISO 10545-2 | ± 0.5% - 0.3% | ± 0.4% | |
| Surface Qualities | ISO 10545-2 | Min 95% | <95% | |
| Water Absorption | ISO 10545-3 | 0.5% < E ≤ 3% | ≤ 1% | |
| Breaking load in N | ISO 10545-4 | 700 min | > 1800 | |
| Bending Strength in N/mm2 | ISO 10545-4 | 12 min | > 50 N/mm2 | |
| Abrasion Resistance | ISO 10545-7 | - | On request | |
| Impact Resistance | ISO 10545-5 | - | > 0.6 | |
| Coefficient of Linear Thermal Expansion | ISO 10545-8 | - | < 5 10 ⁻⁶ /°C | |
| Thermal Shock Resistance | ISO 10545-9 | - | Guaranteed | |
| Moisture Expansion | ISO 10545-10 | - | < 0.04% | |
| Crazing Resistance | ISO 10545-11 | - | Guaranteed | |
| Coefficient of Friction | BCRA | > 0.40% | - | |
| Stain Resistance | ISO 10545-14 | GB min | 3 min | |
| Household Chemical Resistance | ISO 10545-13 | - | GB min | |
| Acid & Alkali Resistance (diluted/concentrated) | ISO 10545-13 | - | GLB min | |
| Lead and Cadmium Release | ISO 10545-15 | - | On request | |
| Fire Resistance | - | Decisione 96/603/CE | Class A1 | |
| | | | | |

Certifications





